



Standard Specification for Low-Alloy Steel Deformed and Plain Bars for Concrete Reinforcement¹

This standard is issued under the fixed designation A706/A706M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 *General*—This specification covers deformed and plain low-alloy steel bars in cut lengths or coils for concrete reinforcement intended for applications where restrictive mechanical properties and chemical composition are required for compatibility with controlled tensile property applications or to enhance weldability. The standard sizes and dimensions of deformed bars and their number designations are given in [Table 1](#). The text of this specification references notes and footnotes that provide explanatory material. These notes and footnotes, excluding those in tables, shall not be considered as requirements of this specification.

1.2 *Grade*—Bars are of two minimum yield strength levels: namely, 60 000 psi [420 MPa] and 80 000 [550], designated as Grade 60 [420] and Grade 80 [550], respectively.

NOTE 1—Bars designated as Grade 80 [550], which were introduced in the A706/A706M – 09a revision, may be outside consideration of consensus design codes and specifications.

1.3 Plain bars, in sizes up to and including 2½ in. [63.5 mm] in diameter in coils or cut lengths, when ordered, shall be furnished under this specification. For ductility properties (elongation and bending), test provisions of the nearest smaller nominal diameter deformed bar size shall apply.

1.4 *Controlled Tensile Properties*—This specification limits mechanical properties ([Table 2](#)) to provide the desired yield/tensile properties for controlled tensile property applications.

1.5 *Welding*—This specification limits chemical composition ([6.2](#)) and carbon equivalent ([6.4](#)) to enhance the weldability of the material. When steel is to be welded, a welding procedure suitable for the chemical composition and intended use or service should be used. The use of the latest edition of [AWS D1.4/D1.4M](#) is recommended. This document describes the proper selection of the filler metals, preheat/interpass temperatures, as well as, performance and procedure qualification requirements.

1.6 This specification is applicable for orders in either inch-pound units (Specification A706) or in SI units [Specification A706M].

1.7 The values stated in either inch-pound units or SI units are to be regarded as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with this specification.

1.8 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- [A6/A6M](#) Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling
- [A370](#) Test Methods and Definitions for Mechanical Testing of Steel Products
- [A510](#) Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel
- [A510M](#) Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel (Metric)
- [A615/A615M](#) Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement
- [A700](#) Practices for Packaging, Marking, and Loading Methods for Steel Products for Shipment
- [A751](#) Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products
- [E29](#) Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

2.2 AWS Standard:³

- [AWS D1.4/D1.4M](#) Structural Welding Code—Reinforcing Steel

¹ This specification is under the jurisdiction of ASTM Committee [A01](#) on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee [A01.05](#) on Steel Reinforcement.

Current edition approved Nov. 15, 2009. Published December 2009. Originally approved in 1974. Last previous edition approved in 2009 as A706/A706M – 09a. DOI: 10.1520/A0706_A0706M-09B.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American Welding Society (AWS), 550 NW LeJeune Rd., Miami, FL 33126, <http://www.aws.org>.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Deformed Bar Designation Numbers, Nominal Weights [Masses], Nominal Dimensions, and Deformation Requirements

Bar Designation No.	Nominal Weight, lb/ft [Nominal Mass, kg/m]	Nominal Dimensions ^A			Deformation Requirements, in. [mm]		
		Diameter, in. [mm]	Cross-Sectional Area in. ² [mm ²]	Perimeter, in. [mm]	Maximum Average Spacing	Minimum Average Height	Maximum Gap (Chord of 12.5 % of Nominal Perimeter)
3 [10]	0.376 [0.560]	0.375 [9.5]	0.11 [71]	1.178 [29.9]	0.262 [6.7]	0.015 [0.38]	0.143 [3.6]
4 [13]	0.668 [0.994]	0.500 [12.7]	0.20 [129]	1.571 [39.9]	0.350 [8.9]	0.020 [0.51]	0.191 [4.9]
5 [16]	1.043 [1.552]	0.625 [15.9]	0.31 [199]	1.963 [49.9]	0.437 [11.1]	0.028 [0.71]	0.239 [6.1]
6 [19]	1.502 [2.235]	0.750 [19.1]	0.44 [284]	2.356 [59.8]	0.525 [13.3]	0.038 [0.97]	0.286 [7.3]
7 [22]	2.044 [3.042]	0.875 [22.2]	0.60 [387]	2.749 [69.8]	0.612 [15.5]	0.044 [1.12]	0.334 [8.5]
8 [25]	2.670 [3.973]	1.000 [25.4]	0.79 [510]	3.142 [79.8]	0.700 [17.8]	0.050 [1.27]	0.383 [9.7]
9 [29]	3.400 [5.060]	1.128 [28.7]	1.00 [645]	3.544 [90.0]	0.790 [20.1]	0.056 [1.42]	0.431 [10.9]
10 [32]	4.303 [6.404]	1.270 [32.3]	1.27 [819]	3.990 [101.3]	0.889 [22.6]	0.064 [1.63]	0.487 [12.4]
11 [36]	5.313 [7.907]	1.410 [35.8]	1.56 [1006]	4.430 [112.5]	0.987 [25.1]	0.071 [1.80]	0.540 [13.7]
14 [43]	7.65 [11.38]	1.693 [43.0]	2.25 [1452]	5.32 [135.1]	1.185 [30.1]	0.085 [2.16]	0.648 [16.5]
18 [57]	13.60 [20.24]	2.257 [57.3]	4.00 [2581]	7.09 [180.1]	1.58 [40.1]	0.102 [2.59]	0.864 [21.9]

^A The nominal dimensions of a deformed bar are equivalent to those of a plain round bar having the same weight [mass] per foot [metre] as the deformed bar.

TABLE 2 Tensile Requirements

	Grade 60 [420]	Grade 80 [550]
Tensile strength, min, psi [MPa]	80 000 [550] ^A	100 000 [690] ^A
Yield strength, min, psi [MPa]	60 000 [420]	80 000 [550]
Yield strength, max, psi [MPa]	78 000 [540]	98 000 [675]
Elongation in 8 in. [200 mm], min, %		
Bar Designation Nos.		
3, 4, 5, 6 [10, 13, 16, 19]	14	12
7, 8, 9, 10, 11 [22, 25, 29, 32, 36]	12	12
14, 18 [43, 57]	10	10

^A Tensile strength shall not be less than 1.25 times the actual yield strength.

2.3 Government Standard:⁴

MIL-STD-129 Marking for Shipment and Storage

2.4 U.S. Federal Standard:⁴

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *deformations, n*—transverse protrusions on a deformed bar.

3.1.2 *deformed bar, n*—steel bar with protrusions; a bar that is intended for use as reinforcement in reinforced concrete and related construction.

3.1.2.1 *Discussion*—The surface of the bar is provided with lugs or protrusions that inhibit longitudinal movement of the bar relative to the concrete surrounding the bar in such construction. The lugs or protrusions conform to the provisions of this specification.

3.1.3 *plain bar, n*—steel bar without protrusions.

3.1.4 *rib, n*—longitudinal protrusions on a deformed bar.

4. Ordering Information

4.1 It shall be the responsibility of the purchaser to specify all requirements that are necessary for material ordered to this specification. Such requirements shall include, but are not limited to, the following:

4.1.1 Quantity (weight) [mass],

4.1.2 Name of material (low-alloy steel deformed and plain bars for concrete reinforcement),

4.1.3 Size,

4.1.4 Grade,

4.1.5 Cut lengths or coils,

4.1.6 Deformed or plain,

4.1.7 Packaging (see Section 17), and

4.1.8 ASTM designation and year of issue.

5. Material and Manufacture

5.1 The bars shall be processed from properly identified heats of mold-cast or strand-cast steel.

5.2 The steel shall be made by one of the following processes: electric-furnace, basic-oxygen, or open-hearth.

6. Chemical Composition

6.1 The chemical analysis of each heat shall be determined in accordance with Test Methods A751. The manufacturer shall make the analysis on test samples taken preferably during the pouring of the heat. The percentages of carbon, manganese, phosphorus, sulfur, silicon, copper, nickel, chromium, molybdenum, and vanadium shall be determined.

6.2 The chemical composition as shown by heat analysis shall be limited by the following:

Element	max, %
Carbon	0.30
Manganese	1.50
Phosphorus	0.035
Sulfur	0.045
Silicon	0.50

6.3 Choice and use of alloying elements, combined with carbon, phosphorus, and sulfur to produce the mechanical properties prescribed in Table 2 and Table 3, shall be made by the manufacturer. Elements commonly used include manganese, silicon, copper, nickel, chromium, molybdenum, vanadium, columbium, titanium, and zirconium.

TABLE 3 Bend Test Requirements

Bar Designation No.	Pin Diameter for 180° Bend Tests	
	Grade 60 [420]	Grade 80 [550]
3, 4, 5 [10, 13, 16]	3d ^A	3½ d ^A
6, 7, 8 [19, 22, 25]	4d	5d
9, 10, 11 [29, 32, 36]	6d	7d
14, 18 [43, 57]	8d	9d

^A d = nominal diameter of specimen.

⁴ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, http://www.dodssp.daps.mil.



6.4 The heat analysis shall be such as to provide a carbon equivalent (C.E.) not exceeding 0.55 % as calculated by the following formula:

$$\text{C.E.} = \% \text{C} + \frac{\% \text{Mn}}{6} + \frac{\% \text{Cu}}{40} + \frac{\% \text{Ni}}{20} + \frac{\% \text{Cr}}{10} - \frac{\% \text{Mo}}{50} - \frac{\% \text{V}}{10} \quad (1)$$

6.5 *Product (Check) Verification Analysis*—A product check analysis made by the purchaser shall not exceed the following percentages:

Element	max, %
Carbon	0.33 %
Manganese	1.56 %
Phosphorus	0.043 %
Sulfur	0.053 %
Silicon	0.55 %

7. Requirements for Deformations

7.1 Deformations shall be spaced along the bar at substantially uniform distances. The deformations on opposite sides of the bar shall be similar in size, shape, and pattern.

7.2 The deformations shall be placed with respect to the axis of the bar so that the included angle is not less than 45°. Where the line of deformations forms an included angle with the axis of the bar from 45 to 70°, inclusive, the deformations shall reverse alternately in direction on each side, or those on one side shall be reversed in direction from those on the opposite side. Where the line of deformation is over 70°, a reversal in direction shall not be required.

7.3 The average spacing or distance between deformations on each side of the bar shall not exceed $\frac{7}{10}$ of the nominal diameter of the bar.

7.4 The overall length of deformations shall be such that the gap (measured as a chord) between the ends of the deformations shall not exceed 12.5 % of the nominal perimeter of the bar. Where the ends terminate in a rib, the width of the rib shall be considered as the gap between these ends. The summation of the gaps shall not exceed 25 % of the nominal perimeter of the bar. The nominal perimeter of the bar shall be 3.1416 times the nominal diameter.

7.5 The spacing, height, and gap of deformations shall conform to the requirements prescribed in [Table 1](#).

8. Measurements of Deformations

8.1 The average spacing of deformations shall be determined by measuring the length of a minimum of 10 spaces and dividing that length by the number of spaces included in the measurement. The measurement shall begin from a point on a deformation at the beginning of the first space to a corresponding point on a deformation after the last included space. Spacing measurements shall not be made over a bar area containing bar marking symbols involving letters or numbers.

8.2 The average height of deformations shall be determined from measurements made on not less than two typical deformations. Determinations shall be based on three measurements per deformation, one at the center of the overall length and the other two at the quarter points of the overall length.

8.3 Insufficient height, insufficient circumferential coverage, or excessive spacing of deformations shall not constitute cause for rejection unless it has been clearly established by

determinations on each lot (see [Note 2](#)) tested that typical deformation height, gap, or spacing do not conform to the minimum requirements prescribed in [Section 7](#). No rejection shall be made on the basis of measurements if fewer than ten adjacent deformations on each side of the bar are measured.

NOTE 2—As used within the intent of [8.3](#), the term “lot” shall mean all the bars of one bar size and pattern of deformations contained in an individual shipping release or shipping order.

9. Mechanical Requirements

9.1 Tensile Properties:

9.1.1 The material, as represented by the test specimens, shall conform to the requirements for tensile properties prescribed in [Table 2](#). The yield strength or yield point shall be determined by one of the following methods:

9.1.1.1 Offset method (0.2 % offset) as described in Test Methods and Definitions [A370](#). A second tensile test result shall also be required. In addition, the stress corresponding to a tensile strain of 0.0035 shall be a minimum of 60 000 psi [420 MPa] for Grade 60 [420] and a minimum of 80 000 psi [550 MPa] for Grade 80 [550]. The value of stress corresponding to a tensile strain of 0.0035 shall be reported in the test report ([13.1.3](#)).

9.1.1.2 By the drop of the beam or halt in the gage of the tensile testing machine, where the steel tested has a sharp-knead or well-defined type of yield point.

9.1.2 The percentage of elongation shall be as prescribed in [Table 2](#).

9.2 Bending Properties:

9.2.1 The bend test specimen shall withstand being bent around a pin without cracking on the outside radius of the bent portion. The requirements for degree of bending and sizes of pins are prescribed in [Table 3](#). When material is furnished in coils, the test specimen shall be straightened prior to placing it in the bend tester.

9.2.2 The bend test shall be made on specimens of sufficient length to ensure free bending and with apparatus that provides:

9.2.2.1 Continuous and uniform application of force throughout the duration of the bending operation,

9.2.2.2 Unrestricted movement of the specimen at points of contact with the apparatus and bending around a pin free to rotate,

9.2.2.3 Close wrapping of the specimen around the pin during the bending operation.

9.3 Test Specimens:

9.3.1 The tension test specimens shall be the full section of the bar as rolled. The unit stress determination shall be based on the nominal bar area.

9.3.2 The bend test specimens shall be the full section of the bar as rolled.

9.3.3 When material is furnished in coils, the test specimen shall be taken from the coil and straightened prior to placing it in the jaws of the tensile machine. Straightening of the test specimen shall be done carefully to avoid formation of local sharp bends and to minimize cold work. (See [Note 3](#).)

9.3.3.1 Test specimens taken from post-fabricated material shall not be used to determine conformance to this specification.

NOTE 3—Insufficient straightening prior to attaching the extensometer can result in lower-than-actual yield strength readings. Multiple bending distortion from mechanical straightening and fabricating machines can lead to excessive cold work, resulting in higher yield strengths, lower elongation values, and a loss of deformation height.

10. Permissible Variation in Weight [Mass]

10.1 Deformed reinforcing bars shall be evaluated on the basis of nominal weight [mass]. The weight [mass] determined using the measured weight [mass] of the test specimen and rounding in accordance with Practice E29, shall be at least 94 % of the applicable weight [mass] per unit length prescribed in Table 1. In no case shall overweight [excess mass] of any deformed bar be cause for rejection.

10.2 Weight [mass] variation for plain bars shall be computed on the basis of permissible variation in diameter. For plain bars smaller than $\frac{3}{8}$ in. [9.5 mm] in diameter, use Specification A510 [Specification A510M]. For larger bars up to and including $2\frac{1}{2}$ in. [63.5 mm] in diameter, use Specification A6/A6M.

11. Finish

11.1 The bars shall be free of detrimental surface imperfections.

11.2 Rust, seams, surface irregularities, or mill scale shall not be cause for rejection, provided the weight, dimensions, cross-sectional area, and tensile properties of a hand wire brushed test specimen are not less than the requirements of this specification.

11.3 Surface imperfections or flaws other than those specified in 11.2 shall be considered detrimental when specimens containing such imperfections fail to conform to either tensile or bending requirements. Examples include, but are not limited to, laps, seams, scabs, slivers, cooling or casting cracks, and mill or guide marks.

NOTE 4—Deformed reinforcing bars intended for epoxy coating applications should have surfaces with a minimum of sharp edges to achieve proper coverage. Particular attention should be given to bar marks and deformations where coating difficulties are prone to occur.

NOTE 5—Deformed reinforcing bars destined to be mechanically-spliced or butt-welded may require a certain degree of roundness in order for the splices to adequately achieve strength requirements.

12. Number of Tests and Retests

12.1 All mechanical tests shall be conducted in accordance with Test Methods and Definitions A370 including Annex A9.

12.2 *Number of Tests*—One tension test, one bend test, and one set of dimensional property tests including bar weight [mass] and spacing, height, and gap of deformations shall be made of each bar size rolled from a heat.

12.3 Retests:

12.3.1 If the results of an original tension specimen fail to meet the specified minimum requirements and are within 2000 psi [14 MPa] of the required tensile strength, within 1000 psi [7 MPa] of the required yield strength, or within two percentage units of the required elongation, a retest shall be permitted on two random specimens for each original tension specimen failure from the lot. Both retest specimens shall meet the requirements of this specification.

12.3.2 If a bend test fails for reasons other than mechanical reasons or flaws in the specimen as described in 12.3.4.2 and 12.3.4.3, a retest shall be permitted on two random specimens from the same lot. Both retest specimens shall meet the requirements of this specification. The retest shall be performed on test specimens that are at air temperature but not less than 60°F [16°C].

12.3.3 If a weight [mass] test fails for reasons other than flaws in the specimen as described in 12.3.4.3, a retest shall be permitted on two random specimens from the same lot. Both retest specimens shall meet the requirements of this specification.

12.3.4 If the original test or any of the random retests fails because of any reasons listed in 12.3.4.1, 12.3.4.2, or 12.3.4.3, the test shall be considered an invalid test:

12.3.4.1 The elongation property of any tension test specimen is less than that specified, and any part of the fracture is outside the middle half of the gage length, as indicated by scribe marks on the specimen before testing;

NOTE 6—Marking specimens with multiple scribe or punch marks can reduce the occurrence of fracture outside or near these marks and the need for declaring the test invalid.

12.3.4.2 Mechanical reasons such as failure of testing equipment or improper specimen preparation; and

12.3.4.3 Flaws are detected in a test specimen, either before or during the performance of the test.

12.3.5 The original results from sections 12.3.4.1, 12.3.4.2, or 12.3.4.3 shall be discarded and the test shall be repeated on a new specimen from the same lot.

13. Test Reports

13.1 The following information shall be reported on a per heat basis. Report additional items as requested or desired.

13.1.1 Chemical analysis including carbon, manganese, phosphorous, sulfur, silicon, copper, nickel, chromium, molybdenum, and vanadium.

13.1.2 Carbon equivalent in accordance with 6.4.

13.1.3 Tensile properties.

13.1.4 Bend test.

13.2 A Material Test Report, Certificate of Inspection, or similar document printed from or used in electronic form from an electronic data interchange (EDI) transmission shall be regarded as having the same validity as a counterpart printed in the certifier's facility. The content of the EDI transmitted document must meet the requirements of the invoked ASTM standard(s) and conform to any EDI agreement between the purchaser and the supplier. Notwithstanding the absence of a signature, the organization submitting the EDI transmission is responsible for the content of the report.

NOTE 7—The industry definition invoked here is: EDI is the computer to computer exchange of business information in a standard format such as ANSI ASC X12.

14. Inspection

14.1 The inspector representing the purchaser shall have free entry, at all times while work on the contract of the purchaser is being performed, to all parts of the manufacturer's works that concern the manufacture of the material ordered.



The manufacturer shall afford the inspector all reasonable facilities to satisfy the inspector that the material is being furnished in accordance with this specification. All tests (except product (check) analysis) and inspection shall be made at the place of manufacture prior to shipment, unless otherwise specified, and shall be so conducted so as not to interfere unnecessarily with the operation of the works.

14.2 *For Government Procurement Only*—Except as otherwise specified in the contract, the contractor shall be responsible for the performance of all inspection and test requirements specified herein and shall be permitted to use one's own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless disapproved by the purchaser at the time of purchase. The purchaser shall have the right to perform any of the inspections and tests at the same frequency as set forth in this specification where such inspections are deemed necessary to assure that material conforms to prescribed requirements.

15. Rejection

15.1 Unless otherwise specified, any rejection based on tests made in accordance with 6.5 shall be reported to the manufacturer within five working days from the receipt of samples by the purchaser.

16. Marking

16.1 When loaded for mill shipment, bars shall be properly separated and tagged with the manufacturer's heat or test identification number.

16.2 Each manufacturer shall identify the symbols of his marking system.

16.3 All bars produced to this specification, except plain round bars, which shall be tagged for grade, shall be identified

by a distinguishing set of marks legibly rolled onto the surface of one side of the bar to denote in the following order:

16.3.1 *Point of Origin*—Letter or symbol established as the manufacturer's mill designation.

16.3.2 *Size Designation*—Arabic number corresponding to bar designation number of Table 1.

16.3.3 *Type of Steel*—Letter W indicating that the bar was produced to this specification, or letters W and S indicating that the bar was produced to meet both this specification and Specification A615/A615M.

16.3.4 *Minimum Yield Strength Designation*—For Grade 60 [420] bars, the marking shall be either the number 60 [4] or a single continuous longitudinal line through at least five spaces offset from the center of the bar. For Grade 80 [550] bars, the marking shall be either the number 80 [6] or three continuous longitudinal lines through at least five spaces.

16.3.5 It shall be permissible to substitute a metric size bar of Grade 420 for the corresponding inch-pound size bar of Grade 60, and a metric size bar of Grade 550 for the corresponding inch-pound size bar of Grade 80.

17. Packaging and Package Marking

17.1 Packaging, marking, and loading for shipment shall be in accordance with Practices A700.

17.2 When specified in the contract or order, and for direct procurement by or direct shipment to the U.S. Government, marking for shipment, in addition to requirements specified in the contract or order, shall be in accordance with MIL-STD-129 for military agencies and with Fed. Std. No. 123 for civil agencies.

18. Keywords

18.1 alloy steel; concrete reinforcement; deformations (protrusions); steel bars

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A706/A706M – 09a) that may impact the use of this standard. (Approved Nov. 15, 2009.)

(1) Revised 9.1.1.1.

Committee A01 has identified the location of selected changes to this standard since the last issue (A706/A706M – 09) that may impact the use of this standard. (Approved Oct. 1, 2009.)

(1) Added Grade 80 [550] to the specification.

(2) Revised 1.2, 16.3, 16.3.4, 16.3.5, and Tables 2 and 3.

(3) Added Note 1 and 4.1.4, and renumbered subsequent notes and subsections.

Committee A01 has identified the location of selected changes to this standard since the last issue (A706/A706M – 08a) that may impact the use of this standard. (Approved May 1, 2009.)

(1) Deleted Table Footnote A under Table 1 and relabeled subsequent footnotes.

(2) Revised Table 2.

Committee A01 has identified the location of selected changes to this standard since the last issue (A706/A706M – 08) that may impact the use of this standard. (Approved Oct. 1, 2008.)

(1) Revised 9.1.1.1.

Committee A01 has identified the location of selected changes to this standard since the last issue (A706/A706M – 06a) that may impact the use of this standard. (Approved May 1, 2008.)

(1) Revised 9.1.1.1.

(2) Added 9.3.3, 9.3.3.1, and Note 3.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).